

Alvarado, P., Sibaja, M., Jimenes, L., Barreiro, M.F., Cateto, C.A., Rodrigues, A.E., Lopretti, M.,
"Bio-based composite Materials from olive stone" 14th European Biomass Conference and
Exhibition, Paris, France, 17-21 October (2005) (*poster*).


[close window](#) [print window](#)

Proceedings of the 14th European Biomass Conference Biomass for Energy, Industry and Climate Protection

held in Paris, France, 17-21 October 2005

The largest biomass event of 2005, featuring a record number of 1142 Participants from 78 countries from all over the world, the 14th European Biomass Conference and Exhibition represented a first-rate opportunity for exchange of experiences and ideas, dissemination of results, demonstration, application and market implementation of the state-of-the-art products and technologies by the foremost companies in the field, as well as networking and making business valuable contacts.

The great success of this global event underlined the rapidly growing market in energy and products derived from biomass, agricultural residues and energy-rich vegetation and their contribution to alleviate the world's pressing climate and environmental problems.

Containing 593 papers based on the plenary, oral and visual contributions selected by the Scientific Committee for presentation at the Conference, the Conference Proceedings represent an essential reference to everyone involved in the global biomass sector; scientists, policy makers, operators, key actors and industry representatives alike, covering a comprehensive range of topics which include:

- Biomass Resources
- R&D of Bioenergy Conversion Technology Systems. Thermochemical Conversion - Gasification and Pyrolysis
- R&D of Combustion and Co-Combustion and R&D of Biological Conversion and Biofuels Production
- Demonstration and Market Implementation of Bioenergy in the Heat and Electricity Sector - National sector, municipal sector, industry sector, private sector, projects and results, economy of market implementation, directives and needs for directives
- Demonstration and Market Implementation of Bioenergy in the Transportation Sector
- Application of Biomass for Energy and Industrial Products - Private vehicles sector, public bus transport, hybrid systems for ships and trains, ecological cars, jet-biofuel
- Economics and Benefits Deriving from Biomass Process Technologies, Integration and Simultaneous Production. Identification of most promising Bioenergy complexes
- International Biofuels Trade, Strategy, Policy and Climate Protection Issues
- International Co-Operation for Accelerating the Large-Scale Worldwide Deployment of Bioenergy. Biomass in the Developing World

The Conference was jointly organized by ETA-Florence, Italy and WIP-Munich, Germany.

Proceedings published by ETA-Florence, Italy and WIP-Munich, Germany.

Available as:

CD-Rom, 593 papers, English text.

ISBN: 88-89407-07-7



BIO-BASED COMPOSITE MATERIALS FROM OLIVE STONE

Sibaja¹ M., Alvarado¹ P., Jiménez¹ L., Rojas¹ O., Barreiro^{2a} M.F., Catelo^{2a} C.A., Rodrigues^{2b} A.E., Lopretti³ M.

¹ POLIUNA, Universidad Nacional, Ap. 86-3000, Heredia, Costa Rica. Tel: (506) 2773557; Fax: (506) 2773557.

E-mail address: maria.sibaja@gmail.com

² LSRE (a – Instituto Politécnico de Bragança, Portugal, b- Faculdade de Engenharia da Universidade do Porto, Portugal)

³ CIN, Facultad de Ciencias, Universidad de la República, Uruguay

ABSTRACT: The present work describes the methodology used for the preparation and characterization of composite samples prepared by mixing various percentages of olive stone flour in a polyester resin matrix. A study on the chemical-physical properties of the olive stone is reported, as well as, a set of tests to evaluate the mechanical properties of the manufactured products obtained. Biodegradation studies were carried out on the obtained composite materials.

Keywords: Olive residues, Composites, Bio-materials.

1 INTRODUCTION

Olive oil extraction industry generates large amounts of residues. These by-products are formed, essentially, by a liquid effluent (vegetation water) and a solid residue composed by olive skin, stone, seed and water; usually designated by cake. The characteristics of the obtained cakes depend on the extraction process used, namely, they differ on the moisture content. Figure 1 presents a summary of the extraction processes used and the corresponding by-products. The stone extraction, in the two-phase process, is also indicated. The terminology press-cake, cake and sludges was used to distinguish the three types of solid residues. The press-cake is obtained from the traditional press process, the cake from the continuous three-phase process and the sludges from the continuous two-phase process. The moisture content of the press-cake, cake and sludges is, 27, 50 and 57 percent, respectively [1].




Figure 1. Olive oil extraction processes and related by-products.

Olive stone, a lignocellulosic material, is currently used mainly as energy source. Recently, we can find in the literature references to its use as a raw material to produce activated carbon [2] and furfural [3] and as heavy metal biosorbent [4]. Steam-explosion was also applied to this material in order to separate the main components: cellulose, hemicellulose and lignin [5].

Despite, the widely use of lignocellulosic materials as reinforcing agents or as fillers in polymer composites, we found in literature very few applications using olive stone. Both thermoset [6, 7] and thermoplastic [8] resins have been proposed to produce olive stone based composites.

The present work describes the methodology used for the preparation and characterization of composite samples prepared by mixing various percentages of olive stone flour in a polyester resin matrix. The effect of the olive stone content on the thermal properties of a composite material using a polyester resin as a matrix was evaluated. In addition, the incidence of accelerated aging effect on their properties was studied.

2 MATERIALS AND METHODS

2.1 Materials

The olive stone was supplied by an olive oil extraction plant (Azeites Milénium LDA, Mirandela, Portugal) and was obtained from a continuous two-phase process. It consists of a granular material (fragments with an average size of 2-5 mm) with a low contamination of skin and seeds (Figure 2). This material was grounded before use.




Figure 2. Sludges obtained from a 2-phase process (A), the extracted olive stone (B) and the residual sludges free of stone (C).

The polyester resin with a content of 41±2 percent of styrene (RESINMEX MR-227) and the methyl ethyl ketone peroxide (used as catalyst) were supplied by FIBROCENTRO (San José, Costa Rica). They were used as received.

2.2 Sample preparation

Samples were prepared by mixing different percentages

Introduction

•Olive oil extraction industry generates a huge amount of residues. These by-products include a liquid effluent (vegetation water) and a solid residue formed by olive skin and stone. Figure 1 shows schematically the three processes currently used (traditional pressing process, continuous two phase process and continuous three phase process) and the corresponding residues.

•Olive stone is a lignocellulosic material mainly used as energy source.

•Some other applications have been proposed, such as production of activated carbon.





Fig. 1. Olive oil extraction industrial process

Olive stone could be used as a filler to make composite materials. Using natural materials, it is possible to make a low cost materials which can have a significant impact on environment.

Experimental



•The biodegradation of composite materials biodegradation of the samples was studied using soil with a mixed culture of *gloeophyllum trabeum* and *phanerochaetes chrysosporium* (50% each).

•Samples were incubated at 30 °C for 30 days and observed daily and control the colonization of the micelio on the polyester, following a methodology similar to that of Ferreira da Silva (9)


Results

Proximate analysis of Olive Stone residues

Analysis	Method ASTM	Results
% Humidity	D1102	8,06
% Ash	D1102	0,52
%Ciclohexane ethanol extracts	D1107	2,1
% Cold water solubility	D1110	1,50
% Holocellulose	D1104	71,53
% lignin	D1106	55,8
Density (g/cm ³)	D 792	1,67

Density of composite materials

Olive Stone (%)	Density (g/cm ³)	
	No ageing	192 hrs. ageing
0	1,25	0,82
8	1,24	1,08
11	1,24	0,83
15	1,20	1,12
18	1,22	1,22



Effect of the content of seed of olive in the resistance to the impact

Amount of CO₂ produced during the assay

Olive stone (%)	% degradation	m moles CO ₂ produced	
		15 days	30 days
0	0	0,10	0,40
11	10	0,45	0,85
15	20	0,50	0,85
18	20	0,60	0,90

Glass transition temperature (T_g) of polyesters reinforced, to the being put under 192h of aging

Olive Stone (%)	T _g (°C)	
	No ageing	192 hrs. ageing
0	88	114
8	91	117
11	90	105
15	85	102
18	89	103

Temperature media of decomposition (T_{dm}) of polyesters reinforced with different percentage from pressed olive stone

Olive stone (%)	T _{dm} (°C)	
	No ageing	192 hrs ageing
0	404	395
8	409	405
11	381	408
15	386	406
18	382	406

Degrading inoculum of *G. trabeum* and *P. chrysosporium* and *P. ostreatus*

Olive Stone (%)	t ₀	t _{15 days}	t _{30 days}
11	A ₂₈₀	-	A ₂₅₄
11	-	-	A ₂₅₄ , A ₂₈₀
15	A ₂₈₀	-	-
15	A ₂₈₀	A ₂₅₄	A ₂₈₀ , A ₃₁₀ , A ₂₅₄
18	-	A ₂₅₄	A ₃₁₀ , A ₃₅₂
18	-	A ₂₅₄	A ₂₈₀ , A ₃₁₀ , A ₂₅₄

Conclusions

The experimental results show composite materials with a heterogeneous distribution with matrix, reason for which the properties exhibited by these materials are not good enough to be used in the plastic making industry. Nevertheless, it is important to mention that these materials, although do not reinforce the matrix can be used like fillings in order to contribute with the environmental diminution produced by them. It is necessary to carry on further studies to obtain a more homogeneous material in order to study the effect of the olive stone content in their mechanical properties.

Acknowledgment

Researchers want to acknowledge the support of CYTED IV.17 project and to the Ministry of Science and Technology of Costa Rica.